

Experimental Study on Partial Replacement of cement by Fly Ash with Glass Fiber Reinforcement

Senthi Rajan M¹, V. Keerthana², B. Senthil Naathan³

^{1,3} Assistant Professor, Dept. of Civil Engineering, Dr N G P Institute of Technology, Coimbatore, Tamil Nadu, India

² Assistant Professor, Dept. of Civil Engineering, Kongunadu College of Engineering and Technology, Namakkal, TamilNadu, India.

ABSTRACT: Fly ash can be used as a mineral admixture in cement and concrete. Using it provides several advantages such as improved strength and workability properties, and environmental benefits related to the disposal of waste materials and to reduced carbon dioxide emissions. Alkali Resistant glass fibers are used as additional reinforcement of constant 0.4% by weight of cement. Glass fibers acted as a good crack arrester and increases split and flexural strength, but not show good results in compressive strength.

M₂₀ grade of concrete is used for this study. The main objective of this work is to study the suitability of the fly ash as a mineral admixture for cement replacement and additional reinforcement of glass fibers in concrete. Fly ash as partial replacement of cement and glass fibers are used as additional reinforcement which satisfies the various structural properties of concrete like compressive, split tensile and flexural strength. From the entire study it is concluded that mix M1 (40%FA + 0.4 % of GF) is the best combination among all mixes, which gives maximum tensile strength. There is no increased compressed strength at 7 days and split tensile strength in fly ash mixes.

Keywords: Fly ash (FA), Alkali Resistant Glass Fiber (GF), Workability, Compressive strength, Split tensile strength, Flexural Strength.

I.INTRODUCTION

Sustainable development and produce a greener concrete material in the construction industry requires the utilization of industrial and agricultural waste materials. Now a day, for a number of reasons, the concrete construction industry is not sustainable. Mainly, it requires very large amount of virgin materials which can again require for next generations. Secondly, the main binding material in concrete is Portland cement, in the production of Portland cement produces huge amount of Carbon dioxides, this is a main reason to green house gas effects, emissions of carbon dioxides in manufacturing of Portland cements are causing global warming and climate change. Then another important criteria is, so many concrete structures suffer from durability problems which may waste the natural resources. So, implementing a solution to use a industrial and agricultural waste products for partial replacement of the port land cement, It seems to be suitable solution for sustainable

Development for present and future days. Recycling and reuse of waste materials contribute to energy savings in cement manufacturing, natural resources protection, and to protection of the environment from greenhouse gas effect from minimises the emissions of carbondioxide. Then other reasons are, the proper utilization of other certain components which are potentially pozzolanic reactivity can significantly improves the certain properties of concrete. One of the most important and suitable resource of mineral admixture among the industrial waste material is fly ash, as it is available in large quantities and it relatively contains a huge amount of silica.

In an ancient time of construction, construction activities were carried out with the help of mudstones from mudstone industry. When the coal is burned in high temperature from thermal plants finally get a finely divided particles of fly ash, fly ash is by product of coal. Fly Ash is a by-product of burned coal from power station some efforts are being taken all over the world to proper utilize of industrial, agricultural waste and mineral by-products as supplementary cementious component to improve the strength, workability and other various properties of concrete. Fly ash is a mineral by product of thermal power station and its finely divided particles. Fly ash exhibits pozzolanic properties same as to naturally available pozzolanic materials. Fly ash contain concrete offers economical as well as technical benefits to the structural concrete and also fly ash concrete provide social benefits to the society to decrease the fly ash directly dispose to the environment and minimize the emission of carbon dioxide to the environment. Class F fly ash is used in this experimental investigation collected from Orient Green Power Plant Private limited Pollachi.

Fiber reinforced concrete is a mixture of mainly port land cement, fine aggregate, coarse aggregate, water and addition of fibers. Fiber reinforced concrete is relatively new material, in fiber reinforced concrete, small length of fibers are dispersed randomly throughout the mix. The variety number of natural and artificial types of fibers is available in market the artificial fibers are mainly glass fiber, steel fibers, recrons and organic polymers etc. When the fibers are present in concrete mixes it will acts as crack arresters and improves the tensile and flexural strength of fibers. Compared to the

normal concrete mixes means, concrete having only cement, fine aggregate, coarse aggregate and water, fiber reinforced concrete increases the strength in terms of flexure and tensile strength.

C. OBJECTIVES.

The main objectives of this experimental investigation are as follows.

- ┌ To study the various properties of fly ash used as mineral admixture for partial cement replacement and glass fiber is used as additional reinforcement.
- ┌ To study the workability properties of concrete when cement is partially replaced with fly ash and increase the percentage of glass fibers in concrete.
- ┌ To study the various mechanical properties of concrete such as compressive, split tensile and flexural properties of this study.
- ┌ Use of industrial waste in use full manner to reduce the disposal problem in present and future days and significantly reduce the CO₂ emission and also avoid adverse effect environment, provide economic construction material to the construction industry .

II. LITERATURE REVIEW

Saiful M, et al. (2010), This paper reports the results of an experimental investigation carried out to study the effects of fly ash on strength development of mortar and the optimum use of fly ash in mortar. Cement was partially replaced with six percentages 10%, 20%, 30%, 40%, 50% and 60% of fly ash by weight. Test results were shows that strength increases with the increase of fly ash up to an optimum value, beyond which, strength values started decreasing. Among the six fly ash mortars, the optimum amount of cement replacement in mortar was about 40%, which provides 14% higher compressive strength and 8% higher tensile strength as compared to OPC mortar. (1)

Srinivasa R, et al. (2010), In this experimental work glass fiber was added to the concrete at 0.03% by concrete volume. Comparison study was carried out to show the effectiveness of with and without glass fibers. The increase in compressive strength for all the grades of concrete mixes was varied from 20 to 25% when compared with 28 days strength. The flexural and split tensile strength for all the grades of concrete mixes was varied from 15% to 20% when compared with 28 days strength. (2)

Pitroda J, et al. (2012), The cement has been replaced by fly ash accordingly in the range of 0% 10%, 20%, 30% & 40% by weight of cement for M-25 and M-40 mix. Result was indicated that FA can be used as cement substitute at 10% replacement at 28 days curing age Compressive strength reduces when cement replaced fly ash. As fly ash percentage increases compressive strength and split strength decreases. (3)

Shamsuddin H, et al. (2012), In this experimental work glass fiber was added to the concrete at 0.03% by concrete volume. Comparison study was carried out to show the effectiveness of with and without glass fibers. It has been

observed that the workability of concrete decreases with the addition of Glass Fibres. Flexural strength, Split tensile strength for M-20, M-30 and M-40 grade of concrete at 3, 7 and 28 days are observed to be 20% to 30%, 25% to 30% and 25% to 30% respectively when compared with 28 days strength of Plain Concrete. (4)

Kartikey T, et al. (2013), He suggested that when the cement is partially replaced with fly ash, fly ash improves the properties of structural concrete. In this work characteristic strength and properties of various grades of concrete were studied, the various grades were M15, M20 and M25 for all this grades fly ash was used with cement at 20%, 40% and 60%. When the cement is partially replaced with fly ash workability of concrete was increased with increased percentage of fly ash. For each grade of concrete three cubes were tested for compressive strength. The optimum strength was obtained for M15 grade was 14.48 N/mm² for 20% replacement, 14 N/mm² for M20 grade at 20% replacement level and 14.05 N/mm² for M25 grade at 20% replacement. From this work finally concluded that fly ash replacement up to 20% shows greater strength than 40% and 60% for all three grades at 28 days of curing period. (5)

III. MATERIALS AND PROPERTIES

A. Cement

Ordinary Portland cement of 43 grade (Chettinad) conforming to IS 8112-1989 was used. Table 1 shows the test results of basic properties of cement.

Table 1: Basic Properties of Cement

Properties	Cement
Specific gravity	3.1
Standard consistency	31%
Initial setting time	38min
Final setting time	480min
Fineness	5.3%

B. Fine Aggregate

M sand of size below 4.75mm conforming to zone II of IS 383-1970 was used as fine aggregate. Table 2 shows the test results of basic properties of fine aggregates.

Table 2: Basic Properties of Fine Aggregates

Properties	Fine Aggregate
Specific gravity	2.43
Water absorption	1.7%

C. Coarse Aggregate

Natural crushed stone with 20mm down size was used as coarse aggregate. Table 3 shows the test results of basic properties of coarse aggregates.

Table 3: Basic Properties of Coarse Aggregates

Properties	Coarse Aggregate
Specific gravity	2.60
Water absorption	1.39%

IV.METHODOLOGY

D. Fly Ash

Class F fly ash was used in this study and it was collected from Green Orient power Plant Private Limited, Pollachi, Coimbatore, Tamil Nadu. Table 4 shows the basic properties of fly ash

Table 4: Basic Properties of Fly Ash

Properties	Fly Ash
Specific gravity	2.3
Fineness	2.28%

E. Glass Fiber

AR Glass fibers of 6mm length fibers are usually round and straight with diameters of 0.014 mm. They could also be bundled together to produce glass fibers bundles with bundle diameters up to 1.3 mm. The Glass fibers used in the present experimental investigation is High Dispersion Cem-FIL AR fibers collected from Sanjay Impex Bangalore.

Table 5: Basic Properties of Glass fiber

Properties	Coarse Aggregate
Specific gravity	2.68
Aspect Ratio	429

F. Water

Ordinary portable water was used in this investigation both for mixing and curing.

G. Concrete Mix Design

Mix proportion used in this study is 1:1.54:2.85 (M20) with water cement ratio 0.5 and glass fibre as 0.4% by weight of cement.

H. Batching and Mixing of Materials

Weight batching and machine mixing are adopted in this experimental work. The percentage replacement of ordinary cement by FA and addition of glass fiber and their material weight are shown in Table 6

Table 6: Mix Proportion per Cubic Metre

Mix Name	GF (gm)	FA (kg)	Cement (Kg)	Fine Aggregate (Kg)	Coarse Aggregate (Kg)	Water (w/c) (liters)
M	-	0	403.908	636.096	1234.414	186
M1	-	121.172	282.7356	636.096	1234.414	186
M2	-	161.563	242.345	636.096	1234.414	186
M3	-	201.954	201.954	636.096	1234.414	186
M4	1.6156	0	403.908	636.096	1234.414	186
M5	1.6156	121.172	282.7356	636.096	1234.414	186
M6	1.6156	161.563	242.345	636.096	1234.414	186
M7	1.6156	201.954	201.954	636.096	1234.414	186

GF – GLASS FIBRE FA – FLY ASH

- └ The main aim of this present work is to study the effects of fly ash as mineral byproduct for partial replacement of cement and glass fiber is additional reinforcement by weight of cement in present investigation. Thus it is an expected that use of fly ash and glass fiber in concrete shows better strength and other properties of concrete.
- └ Class F fly ash is collected from orient green power plant limited collected from Pollachi. Various basic property tests are conducted on fly ash during the progress of the work.
- └ Mixing is done by mechanically operated concrete mixer. During the process of mixing first wet the mixer with ordinary portable water, then add aggregate to mixing drum first, after that adding 25% of total water to the mixer to prevent cement sticking to blades or at the bottom of the drum. Then sand is added, with 25% of water again. After through mixing of aggregates, cement with admixtures if any is added and remaining 50% of water and is added and then AR glass fibers are added to the wet mix.
- └ For each mix slump test is conducted to measure workability. For each proportion 12 cubes of size 150*150*150mm, 3 cylinder of 150mm dia and 300mm in height and 3 beams of 100*100*500mm are casted.
- └ Totally 24cubes, 24cylinder and 24beams are casted. After casting concrete is filled into moulds and compacted. Remoulding was done after 24 hours of casting. Specimens are cured in curing tank. Water immersion method of curing is adopted.
- └ Every proportion cubes, cylinders, beams are casted and tested for compressive, tensile and flexural strength the compressive testing and flexural testing machine. Figure 1 show the concrete placed in moulds.



Fig 1: Moulds filled with concrete

A. Testing of Specimen

Compressive strength test were carried on cubes, split tensile strength test on cylinders and flexural strength test on beams as shown in figure.



Fig 2: Compression Strength Test




Fig 3: Split Tensile Strength Test



Fig 4: Flexural Strength Test

V. RESULTS AND DISCUSSIONS

COMPRESSIVE STRENGTH




PERCENTAGE OF FLY ASH

Fig 5: 7, 28 Days Compressive Strength of fly ash mix

The Fig.5 represents the compressive strength of concrete with partial replacement of cement by fly ash with different percentages. Compressive strength of fly ash is decreased in 7 days curing period than corresponding control concrete mix. At 28 days curing period it gains strength at 30% replacement of fly Ash, at 28 days of curing Compressive strength increased upto 15% replacement of fly ash, after that it gets start to decreasing.

COMPRESSIVE STRENGTH




PERCENTAGE OF FLY ASH AND GLASS FIBER

Fig 6: 14, 28 Days Compressive Strength of FA+GF mix

The above Fig. 6 shows the compressive strength of concrete with partial replacement of fly ash and addition of glass fiber reinforcement by weight of cement. Compressive strength of FA+GF concrete is higher than control concrete. The optimum percentage was obtained at 30% replacement of FA and constant of 0.4% GF at 28 days. In case of 7 days strength is not increased than control mix.


SPLIT TENSILE STRENGTH



PERCENTAGE OF FLY ASH VARIATION

Fig 7: 28 Days Split Tensile Strength of FA mix

The above Fig. 7 shows the 28 days split tensile strength of concrete with partial replacement of fly ash. Split tensile strength of concrete is found to be decreased than that of control mix split tensile strength. The Maximum split tensile strength was observed at 30% fly ash replacement.




PERCENTAGE VARIATION OF GLASS FIBER

Fig 8: 28 Days Split Tensile Strength of FA+GF mix

From the above Fig. 8 shows that fly ash mixes and addition of glass fiber reinforcement shows greater strength than the strength compared to control mix and fly ash mix concrete. Their after strength gets start to decreasing. However, the maximum tensile strength of this mix is obtained at 30%FA + 0.4%GF combinations.

FLEXURAL STRENGTH




PERCENTAGE VARIATION OF FLY ASH

Fig 9: 28 Days Flexural Strength of FA mix

The above Fig. 9 represents the flexural strength of fly ash concrete at 28days. It is observed that flexural strength of fly ash concrete is greater than that of corresponding control mix.

At 10% FA mix shows maximum flexural strength than control mix.


FLEXURAL STRENGTH



PERCENTAGE VARIATION OF FLY ASH AND GLASS FIBER

Fig 10: 28 Days Flexural Strength of GF+FA mix


From the Fig. 10 conclude that FA + GF combination mixes gives optimum strength than control mix and fly ash combination mix. Flexural strength is found to be increased at 30% FA + 0.4%GF combination mixes.



PERCENTAGE OF FLY ASH

Fig. 11: Workability of fly ash concrete mix.

From the above Fig. 11 concludes that workability of fly ash mix concrete goes on increased as the fly ash content increased in concrete mix, because fly ash having more finer particles than cement.



PERCENTAGE OF FLY ASH AND GLASS FIBER

Fig 12: Workability of fly ash and glass fiber concrete mix.

From the Fig. 12 observe that workability of mixes reduced compared with fly mix and control mix, because glass fibers absorbed more water content.

VI. CONCLUSION

Based on experiments and test results on fresh & hardened concrete the following conclusions are drawn

- ⌊ Fly ash content increased in the concrete mix workability of concrete is also increased and FA+GF combination mixes reduces the workability of mixes compared to the fly ash concrete mixes.
- ⌊ The rate of gain in strength of fly ash concrete specimens is observed to be higher than the corresponding conventional concrete at 28 days.
- ⌊ In 7 days strength there is no increased in compressive strength than control mix.
- ⌊ 30% FA and 0.4% GF combination gives good flexural strength than corresponding control mix and fly ash concrete mixes.
- ⌊ 40% FA and 0.4% GF combination gives good tensile strength than corresponding control mix and fly ash concrete mixes.
- ⌊ Use of fly ash reduces the amount of cement content as well as heat of hydration in a concrete mix. Thus, the construction work with fly ash concrete becomes environmentally safe and also economical.

REFERENCES

- 1) Saiful I, Moinul I, (2010), "Strength Behavior of Mortar Using Fly Ash as Partial Replacement of Cement" Concrete Research Letters, Vol. 1 (3), pp 98-106. <http://www.crl.issres.net>
- 2) Srinivasa R, Pannirselvam N, Seshadri T.S, and Sravana P., (2010), "Strength Properties Of Glass Fibre Concrete" ARPN Journal of Engineering and Applied Sciences ISSN 1819-6608 , VOL. 5, Issue 4, pp 1-7.<http://www.arnjournals.com>
- 3) Pitroda J, Zala L.B.,Umrigar F.S, (2012), "Experimental Investigations On Partialreplacement Of Cement With Fly Ash In Designmix Concrete" International Journal of Advanced Engineering Technology E-ISSN 0976-3945 Vol.3, Issue 4, pp 126-129.
- 4) Shamsuddin H.S, Avinash G, Ibrahim Q.S, Mehmood Q.S, Syed A.A, (2012), " Strength Aspects of Glass Fibre Reinforced Concrete" International Journal of Scientific & Engineering ResearchISSN 2229-5518, Volume 3, Issue 7, pp 1-5, <http://www.ijser.org>
- 5) Kartikey T, Jatale A, Khandelwal S, (2013), "Effects On Compressive Strength When Cement Is Partially Replaced By Fly-Ash" IOSR Journal of Mechanical and Civil Engineering (IOSR-JMCE) e-ISSN: 22781684Volume 5, Issue 4, pp 34-43.